

Technical Data Sheet

Decorative coating PERSIA (Gold, White)

Ready-made decorative coating

Decorative coating PERSIA GOLD, PEARL, WHITE allows to create a variety of textures for interiors, applying a variety of application techniques. The combination of small particles of marble and pearlescent base creates an unusually ceremonial, noble appearance.

Properties:

Withstands cleaning with detergents
Has high strength
Changes shades depending on lighting and angle of view
Depending on the technique of application allows to obtain a variety of drawings
Good adhesion
Does not contain organic solvents
Environmentally friendly

Composition:

Substrate	Water-emulsion synthetic copolymer
Pigment	Pearlescent pigments
Reducer	Water

Types of substrates:

It is used for interior works as a decorative coating. Apply to a specially prepared surface.

Surface preparation:

The surface must be firm, dry, free of dust, mud, oil and grease. Previously painted surfaces should be cleaned of old flaking material and cleaned with sandpaper. Places affected by mold or moss should be thoroughly cleaned mechanically and treated with D-07 (TM "ELF") primer or other special means.

Performance of works:

Before starting to work, mix the material of the selected base. It is allowed to add up to 10% of water if necessary. Apply it with roller and block brush. Drying time is 3-4 hours at a temperature of $(20 \pm 2) ^\circ\text{C}$. To increase the hiding power, it is possible to apply the coating in two layers. Recommended operating temperature is not below $+ 5 ^\circ\text{C}$. Clean tools with water after use.

Drying at a temperature of $+ 20 ^\circ\text{C}$ and a relative humidity of 60%

Touch-dry	12 hours
Complete drying out	24 hours
Recommended temperature conditions	from $+ 5 ^\circ\text{C}$ to $+ 30 ^\circ\text{C}$

Components

water	15,00%
filler	50,00%
dispersion	25,00%
conserving agent	0,30%
anti-foaming agent	1,00%
auxiliary materials	8,70%

Technical features:

Coverage rate	4-6 m ² /kg (depending on the application technique)
Non-volatile matter content	55,00%

Solidity	1,3 kg/l at t=20 ⁰ C
Medium	vinyl copolymer
PH	7,5 - 8,5

Recommendations

Precautions	In case of contact with eyes, rinse immediately with plenty of water.
Storage	In a dry and clean place at a temperature from +5 ⁰ C to + 30 ⁰ C, in a sealed package not less than 12 months from the date of manufacture
Packing	1 kg, 5 kg

ATTENTION:

The firm is not responsible for poor-quality results (the occurrence of coating defects) in case of improper application on inappropriate places and surfaces, at the change of conditions of use, as well as the occurrence of a larger expense at using by not recommended methods